Supporting Information

Chemical Structure of Arsenic and Chromium in CCA-Treated Wood: Implications of Environmental Weathering

Peter S. Nico[1], Scott E. Fendorf[2], Yvette W. Lowney[3], Stewart E. Holm[4], and Michael V. Ruby[3]

[1]Chemistry Department, Cal State University, Stanislaus, Turlock, CA
[2]Geological and Environmental Sciences, Stanford University, Stanford, CA
[3]Exponent, Boulder, CO
[4]Georgia-Pacific Corporation, Atlanta, Georgia

One page: one figure

The correlation between the fluorescence intensity of the Cr and As (See Figure) show two distinct data clusters with one cluster corresponding exclusively to the low-density areas of the wood and the other to the high-density areas. Both clusters shows a strong As to Cr linear relationship, r = 0.982 and 0.963, respectively, with identical slopes, m = 0.05 implying a uniform Cr-to-As ratio throughout the wood sample.



Correlation between Cr and As fluorescence intensity (in counts per second) from a 10 x 1mm micro-XAS map of a piece of aged wood.